

## Bjelin Woodura Flooring

Pro Matte Lacquer

Level of use domestic: **EN ISO 10874** Class Heavy Residential (Class 23)



Level of use commercial: **EN ISO 10874** Class Heavy Commercial (Class 33)



Woodura	Hardened Wood
Construction	Engineered wood surface with cured wood composite core and wood backing
Surface treatment	UV cured acrylic

General properties	S	M	XL	XXL	Herringbone A + B
Thickness (mm/inches)	9.2/.362	9.2/.362	11.3/.445	11.3/.445	11.3/.445
Width (mm/inches)	151/5.94	151/5.94	206/8.1	271/10.7	91/3.58
Length (mm/inches)	1170/46.06	2000/78.74	2200/86.6	2378/93.6	546/21.49
Wear layer thickness (mm/inches)	0.6/0.024	0.6/0.024	0.6/0.024	0.6/0.024	0.6/0.024
Micro bevel	long- and short side	long- and short side	long- and short side	long- and short side	long- and short side
Locking system	5G Dry	5G Dry	5G Dry	5G Dry	5G
Boards per box	9	7	4	3	22
m <sup>2</sup> /sqft per box	1.6/17.1	2.1/22.8	1.8/19.51	1.9/20.81	1.09/11.73
m <sup>2</sup> /sqft per pallet	55.7/599.01	95.13/1024.0	87/937	93/999	52.47/564.8
Weight per m <sup>2</sup> (kg/lbs)	9/19.9	9/19.9	11/24	11/24	11/24
Weight per box (kg/lbs)	14.3/31.6	19.1/42	20/44.3	22/47.8	12/26.5

Classification and safety properties	Standard test method	Result
Fire resistance	EN 13501	Bfl-S1 (hardly flammable)
Smoke density	ASTM E662	316 Flaming / 255 non-flaming
Critical radiant flux	ASTM E648	Class I - 0.82 W / cm <sup>2</sup>
Thermal resistance	EN 12664 / 12667	R 0.07 (m <sup>2</sup> x K)/W
Thermal conductivity	ASTM C518	1.2472 Vlu in. /h ft <sup>2</sup> F
Formaldehyde emission	EN 717-1	E1
Carb Phase 2 Compliant	ASTM D6007-14	Yes
Brinell hardness	EN 1534	<b>S M 8 HB   XL XXL Herringbone 10 HB</b> (average value)
Impact resistance	EN 14354	EC3
Thickness swell	EN 13329 / ISO 24336	<b>S M &lt;10%   XL XXL Herringbone &lt;8%</b>
Taber abrasion resistance	EN 14354	>6000 revolutions
Sound transmission loss (STC) 8" slab only	ASTM E336/E413	55
Impact isolation class (IIC) 8" slab only	ASTM E492/E989	55
Slip resistance (COF)	ANSI A137.1/A326.3	wet: 0.73 (average value)

Installation properties	
Installation method	Floating or glue down application
Installation instructions	Download from <a href="http://www.bjelin.com">www.bjelin.com</a>
Underlayment	Foam with CS > 60kPa & CC > 20 kPa (according to EN 16354)*
Care & maintenance Instructions	Download from <a href="http://www.bjelin.com">www.bjelin.com</a>



woodura™



The mark of responsible forestry  
FSC® C140725



\* For demanding applications